DIAMONDSTONE®

DIAMONDSEAL

Moisture tolerant primer with abrasion resistant aliphatic urethane



TECHNIQUEX

DIAMONDSTONE®

DIAMONDSEAL

DiamondSeal consists of an unlimited moisture control system with High-Traffic topcoat urethane applied over a multi-directional grind. It is vacuumed with large HEPA filter vacuums to ensure that all of the fines are removed from the concrete.

DiamondSeal gives the appearance of a naturally wet-looking concrete with a medium-sheen finish. It has excellent abrasion and chemical resistance, coupled with good slip resistance in a natural color.



DIAMONDSEAL FEATURES

- Moisture Tolerant
- Slip Resistant
- UV Resistant
- Chemical Resistant
- Minimal Down Time
- Qualified LEED® Product

DIAMONDSEAL TYPICAL PROPERTIES

Bond Strength (ASTM D-4541) Concrete Failure

Abrasion Resistance (ASTM D-4060) 4.5 mg/Loss

Volume Solids 90%

VOC's 2 gm/ltr

Coefficient of Friction (ASTM D2047) 0.70

DIAMOND-VJF JOINT FILLER TYPICAL PROPERTIES

Compressive Strength (ASTM D-695)	12,000 psi
Tensile Strength (ASTM D-638)	6,500 psi
Elongation at Break (ASTM D-638)	15%
Hardness (Shore D) (ASTM D-2240)	55
Bond Strength (ASTM D-4541) Co	ncrete Failure

The data shown in this document reflect typical results based on laboratory testing under controlled conditions.

Reasonable variations from the data shown above may result.



DIAMONDSEAL

CHEMICAL RESISTANCE

See DiamondStone Chemical Resistance Guide.

CLEANING & MAINTENANCE

See DiamondStone Cleaning Instructions.

SURFACE PREPARATION

Apply only to clean and sound concrete substrates that are free of all coatings, sealers, curing compounds, oils, greases or any other contaminants. New concrete should be cured a minimum of 28 days. Concrete that has been contaminated with chemicals or other foreign matter must be neutralized or removed. Remove any laitance or weak surface layers. Prepare surface by mechanical means to achieve a profile equal to industry standards. All surface irregularities, cracks, expansion joints and control joints should be properly addressed prior to application.

PRECAUTIONS & LIMITATIONS

DiamondStone, LLC recommends the use of slip-resistant with this product. As with any surface, all spills should be removed as soon as possible to prevent a slipping hazard. Refer to Material Safety Data Sheet for detailed safety precautions. Do not apply when concrete temperature is less than 50° F or greater than 100° F. (Material cures slower at cooler temperatures, and working time will be substantially reduced at higher temperatures.) All components should be stored in a dry place at temperatures between 65° F and 85° F. Confirm product performance in specific chemical environment prior to use. Substrate temperature must be at least 5° F above the dew point.

EXCEPTIONS

If DiamondStone resinous systems is specified, the system incorporates unlimited moisture control. If DiamondStone is not specified, the system will meet the basis of design on moisture limitations.

NO-NONSENSE WARRANTY

TECHNIQUEX warrants materials & labor to be free from defects for a period of 5 years from the date of substantial completion of the work, unless otherwise stated in the construction documents.

In the event a defect caused by materials or workmanship appears within the warranty period, Techniquex's liability shall be limited to repair or replacement of the work in the defective area only, or at Techniquex's sole election, refund of a pro-rata portion of the contract price for the defective areas. This is the exclusive remedy against Techniquex for the work performed. Notification of a defect must be given to Techniquex in writing during the warranty period.

This limited warranty is exclusive and in lieu of all other warranties of any kind of nature whatsoever, including but not limited to implied warranties of merchantability and fitness for particular purpose, which are specifically excluded and disclaimed. Any and all remedies against Techniquex for defects are limited by this warranty, and in no event shall Techniquex be liable to owner or others for incidental or consequential damages.